



# aramcoPRIMA<sup>®</sup>

| Yanbu

Test	Unit	Method	aramcoPRIMA <sup>®</sup> 110
<b>Group II</b>			<b>Typical</b>
Appearance		Visual	C&B
Kinematic Viscosity @ 40°C	cSt	D 445	23.3
Kinematic Viscosity @ 100°C	cSt	D 445	4.6
Viscosity Index		D 2270	113
Saturates	wt%	D 2007	98
Sulfur	wt ppm	D 2622	10
Noack Volatility (Procedure B)	wt%	D 5800	14.0
CCS Viscosity @ -20°C	mPa-s	D 5293	900
CCS Viscosity @ -25°C	mPa-s	D 5293	1,500
Pour Point	°C	D 97	-18
Density @ 15°C	Kg/L	D 4052	0.8510
Saybolt Color		D 156	+30
Color	ASTM	D 1500	L 0.5
Flash Point COC	°C	D 92	224
Copper Corrosion 100°C 3hrs		D 130	1a
Total Acid Number	mgKOH/gm	D 974	0.01
Aromatics	wt%	D 2007	1