



aramcoULTRA[®]

| Port Arthur

Test	Unit	Method	aramcoULTRA [®] 6
			Typical
Appearance		Visual	C&B
Kinematic Viscosity @ 40°C, cSt		D 445	32.4
Kinematic Viscosity @ 100°C, cSt		D 445	5.9
Viscosity Index		D 2270	125
Saturates	wt%	D 2007	
Sulfur	wt ppm	D2622	<10
Noack Volatility (Procedure B)	wt%	D 5800	7.6
CCS Viscosity @ -30°C	mPa-s	D 5293	4,050
Pour Point	°C	D 5950	-15
Density @ 15°C	Kg/L	D 4052	0.8400
Saybolt Color		D 156	
Color	ASTM	D 1500	L0.5
Flash Point COC	°C	D 92	230
Copper Corrosion 100°C 3hrs		D 130	
Total Acid Number	mgKOH/gm	D 974	
Aromatics	wt%	D 2007	